

## Technical Data Sheet | DuraBase RLF 150 CV

Red List Free covered baseboard with a height of 150 mm

### Material


Red List Free (RLF)

### Technical Specifications

Base Resin Type: TPE

Properties	Test Method	Values
Specific Gravity	ASTM D 792	1.07 ± 0.02
Shore 'A' Hardness	ASTM D 2240	92±2
Tensile Strength	ISO 527-1	12±2 N/mm <sup>2</sup>
Elongation	ISO-5277-1	>500%
MFI@230°C/2.16 Kg (g/10 min)	ASTM D 1238	1.5±0.2
Moisture (%)	-	0.10 Max

Baseboard



(SCALE - 1:1)

### Duracryl International B.V.

Elandstraat 91  
2901 BK Capelle aan den IJssel  
The Netherlands

**Phone** +31 10 458 85 52  
**Website** [www.duracryl.com](http://www.duracryl.com)  
**Email** [info@duracryl.com](mailto:info@duracryl.com)