

Technical Data Sheet | DuraBase 150 CV

TPE (thermoplastic) covered baseboard with a height of 150 mm (5,9 inch)

Material


TPE (thermoplastic) covered

Technical Specifications

Base Resin Type: TPE

Properties	Test Method	Values
Specific Gravity	ASTM D 792	1.07 ± 0.02
Shore 'A' Hardness	ASTM D 2240	92±2
Tensile Strength	ISO 527-1	12±2 N/mm ²
Elongation	ISO-5277-1	>500%
MFI@230°C/2.16 Kg (g/10 min)	ASTM D 1238	1.5±0.2
Moisture (%)	-	0.10 Max

Baseboard



(SCALE - 1:1)



Duracryl International B.V.
 Elandstraat 91
 2901 BK Capelle aan den IJssel
 The Netherlands

Phone +31 10 458 85 52
Website www.duracryl.com
Email info@duracryl.com

Duracryl International LLC
 2743 Irving Blvd
 Dallas TX 75207
 United States of America

Phone +1 (469) 243 4107
Website www.duracryl.com
Email sales@duracryl.com